




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification ⁶ : C07D 491/04, 493/04, 495/04, G03C 1/72 // (C07D 491/04, 311:00, 209:00) (C07D 4,3/04, 311:00, 307:00) (C07D 495/04, 311:00, 333:00)</p>	A1	<p>(11) International Publication Number: WO 95/05382</p> <p>(43) International Publication Date: 23 February 1995 (23.02.95)</p>
<p>(21) International Application Number: PCT/GB94/01758</p> <p>(22) International Filing Date: 11 August 1994 (11.08.94)</p> <p>(30) Priority Data: 9316857.3 13 August 1993 (13.08.93) GB</p> <p>(71) Applicant: PILKINGTON PLC [GB/GB]; Prescott Road, St. Helens, Merseyside WA10 3TT (GB).</p> <p>(72) Inventors: RICKWOOD, Martin; 6 Lansdowne Road, Southport, Merseyside PR8 6AJ (GB). HEPWORTH, John, David; 2 Carnoustie Close, Fulwood, Preston, Lancashire PR2 7ER (GB). GABBUTT, Christopher, David; 39 Branch Road, Mellor Brook, Blackburn, Lancashire BB2 7NY (GB).</p> <p>(74) Agents: PENDLEBURY, Anthony et al.; Page, White & Farrer, 54 Doughty Street, London WC1N 2LS (GB).</p>		<p>(81) Designated States: AM, AU, BR, BY, CA, CN, CZ, GE, HU, JP, KR, LT, LV, MD, MN, PL, RO, RU, SK, UA, UZ, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).</p> <p>Published <i>With international search report.</i></p>
<p>(54) Title: PHOTOCROMIC HETEROCYCLOCHROMENES</p> <p>(57) Abstract</p> <p>A heterobenzopyran compound of general formula (I), wherein R₁ represents a five-membered heterocyclic group containing one or more hetero atoms and fused either to the f-face or the g-face of the benzo moiety of the benzopyran skeleton, the said heterocyclic group being fused in such a manner that the hetero atom in the heterocyclic group is linked directly to a carbon atom on the said benzo moiety, and, optionally, the said heterocyclic group has fused thereto a further carbocyclic or heterocyclic group or is substituted with a group of formula R₄ as defined below; each of R₂ and R₃, which may be the same or different, independently represents a carbocyclic or heterocyclic group, or R₂ and R₃ taken together with the carbon atom to which they are attached form a carbocyclic or heterocyclic ring system; and R₄ represents a hydrogen atom or a substituent selected from alkyl, alkoxy, aryl, aryloxy, heteroaryl, halogen, substituted or unsubstituted amino, azo, imino, amide, ester, cyano, trifluoromethyl or nitro. The heterobenzopyran compounds of the invention are useful as photochromic transparencies for cars and aircrafts.</p> <div style="text-align: right; margin-top: 20px;">  <p>(I)</p> </div>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

- 1 -

PHOTOCHROMIC HETEROCYCLOCHROMENES

The present invention relates to certain novel photochromic heterobenzopyran compounds, and to articles and compositions containing them.

Photochromism is a well-known physical phenomenon which is observed with certain classes of chemical compounds. A detailed discussion of this phenomenon can be found in "Photochromism : Molecules and Systems", Studies in Organic Chemistry 40, Edited by H. Durr and H. Bouas-Laurent, Elsevier 1990.


Pyran derivatives as a class of compounds are known to be capable of exhibiting a photochromic effect. For example, U.S. Patent No. 5066818 describes a group of novel reversible photochromic naphthopyran compounds having at least one ortho-substituted phenyl group at the 3-position of the pyran ring.

The prior art pyran derived photochromic compounds - as illustrated, for example, in U.S. Patent 5066818 - in the activated state exhibit relatively simple absorbance profiles (e.g. Gaussian and Lorenzian curves) and therefore tend to exhibit relatively pure colours, provided that the photochromic material itself is not coloured. For many commercial applications, typically for use in sunglasses, a more neutral brown or grey colouration is required. In order to achieve a more neutral colouration using the prior art photochromic compounds it is necessary to mix together two or more photochromic compounds. This can present disadvantages, both in terms of cost and in terms of the ease with which the photochromic compounds can be incorporated into the polymeric host material into which they are to be introduced.

- 2 -

We have now found a group of heterobenzopyran compounds which when dispersed into a solution or a polymeric host material and activated with actinic light exhibit a neutral, typically brown, colouration in the activated state.

According to the present invention there is provided a heterobenzopyran compound of general formula (I)




wherein R_1 represents a five-membered heterocyclic group containing one or more hetero atoms and fused either to the f-face or the g-face of the benzo moiety of the benzopyran skeleton, the said heterocyclic group being fused in such a manner that the hetero atom in the heterocyclic group is linked directly to a carbon atom on the said benzo moiety, and, optionally, the said heterocyclic group has fused thereto a further carbocyclic or heterocyclic group or is substituted with a group of formula R_4 as defined below;

each of R_2 and R_3 , which may be the same or different, independently represents a carbocyclic or heterocyclic group, or R_2 and R_3 taken together with the carbon atom to which they are attached form a carbocyclic or heterocyclic ring system; and

- 3 -

R₄ represents a hydrogen atom or a substituent selected from alkyl, alkoxy, aryl, aryloxy, heteroaryl, halogen, substituted or unsubstituted amino, azo, imino, amide, ester, cyano, trifluoromethyl or nitro.

For the avoidance of doubt, throughout this specification, the ring numbering used to describe the benzopyran compounds of the present invention is as follows:-



and the f-face on the benzo moiety of the benzopyran skeleton is the face between carbon atoms 7 and 8, and the g-face is that between carbon atoms 6 and 7 of the said benzo moiety.

Throughout this specification, unless stated otherwise, the term "alkyl" is to be taken to mean an alkyl group having from 1 to 6 carbon atoms. Similarly, the term "alkoxy" is to be taken to mean an alkoxy group having from 1 to 6 carbon atoms.

The heterobenzopyran compounds of the present invention possess extremely complex absorbance profiles (i.e. they have multiple absorbance peaks/shoulders/inflections) and as a consequence they are found to exhibit neutral colours such as browns when incorporated in solutions and polymers.

Some of the compounds in accordance with the invention are obtained as mixtures of isomers which are not readily

- 4 -

separable although in other cases one isomer tends to predominate and can be separated out. In both cases, however, we have found that one obtains the complex absorbance profile mentioned above, so that both the isomeric mixtures and the single isomers exhibit the said neutral, typically brown, colouration.

Preferably, the five membered heterocyclic ring in the group R_1 is a furan ring, a pyrrole ring or a thiophene ring, preferably with the hetero-atom attached to the 7-position of the benzopyran skeleton.

Preferred substituents on the heterocyclic ring in the group R_1 are a benzene ring fused thereto, or a cyclohexane ring fused thereto, or one or more alkyl substituents on the heterocyclic ring.

In the case of the pyrrole ring, the ring nitrogen atom may carry an alkyl substituent, usually a methyl group.


Preferably, the substituents R_2 and R_3 on the pyran ring are chosen from a phenyl group, a 4-trifluoromethyl-phenyl group, a 4-alkoxyphenyl group (preferably 4-methoxyphenyl), a 2,4-di(alkoxy)phenyl group (preferably 2,4-dimethoxyphenyl) or a 4-dialkylamino-phenyl group (preferably 4-dimethylamino-phenyl).

When the R_2 and R_3 substituents together with the carbon atom to which they are attached form a carbocyclic ring system, they are preferably a spiro-dibenzocycloheptenyl substituent, or a spiro-adamantyl substituent or a spiro-norbornyl substituent.

Preferred R_4 groups are hydrogen or alkyl, typically methyl.


- 5 -

The benzopyran compounds of the present invention may be prepared by a general preparative method which is based on the following reaction scheme:-



The preparative methods used to form the hetero benzopyran compounds of the present invention are closely analogous to the methods used to prepare relatively well known photochromic benzo- and naphthopyran compounds. The synthesis of such known benzopyran and naphthopyran compounds is described in detail, for example, by L. Merlini in *Advances in Heterocyclic Chemistry*, 1975, 18, 159, and in a number of patents, for example, U.S. 5066818, U.S. 4990287, U.S. 4980089 and WO 92/09593. Typically, the heterobenzopyrans of the present invention are formed by reacting a hydroxy compound of general formula (III) with a propargyl alcohol of general formula (IV) in the presence of acidic alumina (e.g. Brockmann 1 alumina), trifluoroacetic acid or other like acidic catalyst; the initial condensation/etherification reaction between the hydroxy compound (III) and the propargyl alcohol of formula (IV) is followed by a series of catalysed sigmatropic shifts and tautomerisation to yield the desired compound of general formula (I).

The synthetic process for preparing the heterobenzopyran compounds of the present invention can lead to the formation of two isomeric heterobenzopyrans of formulae (IA) and (IB) as illustrated in the following reaction scheme:-



- 7 -

The reaction of the hydroxy compound (III) with the propargyl alcohol (IV) proceeds via the initial formation of an aryl propargyl ether of formula (V), followed by a Claisen-like [3,3]- sigmatropic re-arrangement. When there are no substituents in the ortho positions on either side of the hydroxy group in the compound of formula (III), the Claisen-like [3,3]-sigmatropic re-arrangement gives rise to two isomeric intermediates of formulae (VIA) and (VIB), and these intermediates then undergo a [1,5]- sigmatropic shift to form the two isomeric heterobenzopyran compounds of formulae (IA) and (IB).

The presence of substituents or fused moieties on the benzene ring of the compound of formula (III) can lead to a predominance of one of the two isomers (IA) and (IB) since the isomeric ratio of the two heterobenzopyran isomers is affected by the regioselectivity of the cyclisation of the aryl propargyl ether of formula (V).

The hydroxy compounds of formula (III) are either commercially available compounds or are prepared using known synthetic methods, or methods derived from these known synthetic methods.

For example, 5-hydroxy-2,3-dimethylbenzothiophene, a starting material in Example 8 below, is made by a method analogous to that described by S. Gronowitz et al. (Acta. Pharm. Suec. 1978, 15, 337) for the preparation of 2-hydroxydibenzothiophene. Thus, 5-bromo-2,3-dimethylbenzothiophene is converted using n-BuLi to the 5-Lithium compound which is reacted with (n-BuO)₃B to form the corresponding tri-butyl borate derivative, which is then treated with H₂O₂ to yield the desired 5-hydroxy-2,3-dimethyl thiophene.

- 8 -

The propargyl alcohols of general formula (IV) which are used to prepare the heterobenzopyran compounds of the present invention are prepared in known manner, e.g. as described by T.F. Rutledge in Acetylenic Compounds, Reinhold, New York 1968.

The novel heterobenzopyran compounds of the present invention are found to be particularly useful as photochromic materials to be incorporated into polymeric host materials so as to impart photochromic properties to the said polymeric host materials.

The photochromic heterobenzopyran compounds of the present invention are incorporated into the plastics host material in known manner, for example as described in European Patent No. 0245020 or U.S. Patent No. 5066818.

The materials of the present invention impart a yellow-brown, red-brown or olive-green colouration in their darkened state. In the faded or bleached condition the materials exhibit a colourless or pale colouration.

Typical polymeric host materials are optically clear polymer materials, such as polymers of polyol(allyl carbonate)-monomers, polyacrylates such as polymethylmethacrylates, cellulose acetate, cellulose triacetate, cellulose acetate propionate, cellulose acetate butyrate, poly(vinyl acetate), poly(vinyl alcohol), polyurethanes, polycarbonates, polyethylene terephthalate, polystyrene, styrene/methylmethacrylate copolymers, styrene/acrylonitrile copolymers, and polyvinylbutyral. Transparent copolymers and blends of the transparent polymers are also suitable as host materials. Polymers of the type described in EP 0294056 or EP 0453149 are also suitable.

- 9 -

Preferably, the polymeric host material is an optically clear polymerized organic material such as a polyurethane or a polymer of diethylene glycol bis(allyl carbonate) (sold under the trade name CR-39), or SPECTRALITE - a material sold by Sola Optical USA.

Usually, the amount of photochromic benzopyran compound incorporated in the polymeric host material ranges from 0.01 to 0.5 wt%, based on the weight of the polymeric host material.

In some applications, it may be desirable or advantageous to combine the heterobenzopyran compounds of the present invention with other photochromic materials to obtain an aggregate colour effect. For example, spiro-oxazine materials may have a colour range of 530 to 680 nm which means that in the darkened condition the spiro-oxazines impart a red-purple or purple or blue or blue-green or green colouration to a host material. Thus, the present heterobenzopyran compounds can be combined with known spiro-oxazine materials such as those described in our European Patent No. 0245020, or in our UK Patent Applications Nos. 92/25346, 92/25347 and 92/25348, or with the spiro (indolino) naphthoxazines, spiro (indolino) pyrido benzoxazines and spiro (indolino) benzoxazines described in U.S. Patents Nos. 4637698, 3562172, 3578602, 4816584, 4215010 and 4342668 in order to modify the colouration in the darkened condition from a brown to a grey. For similar reasons, the compounds of the present invention may also be combined with other photochromic materials such as the naphthopyran compounds described in our UK Patent Application No. 9306587 or in U.S. Patent No. 5066818.

Typically, when used in combination, the further additional photochromic material is present in an amount of from 0.001 to 0.5 weight %, based on the weight of the polymeric host material.

- 10 -


Examples of suitable uses of the photochromic plastic articles incorporating the heterobenzopyran compounds of the invention are in the manufacture of plano lenses, e.g. for sunglasses, and ophthalmic lenses and as photochromic transparencies for vehicles such as cars and aircraft.

The following Examples illustrate the present invention. The structures of the various products were determined using proton NMR.


Example 1

3,3-Dianisyl-3H-[chromeno[6,5-b]benzofuran] (1a) and
3,3-dianisyl-3H-[chromeno[6,7-b]benzofuran] (1b).

A mixture of 2-hydroxydibenzofuran (2.38g; 0.0129mol), 1,1-dianisylprop-2-yn-1-ol (3.35g; 0.0129mol) and acidic Alumina Brockmann I (8.0g) in benzene (150ml) was heated under reflux for 1.5h. The resulting dark mixture was filtered to remove the alumina which was washed with benzene, the combined filtrate and washings were evaporated and the residue flash chromatographed over silica (eluent: 20% ethyl acetate in hexane) to give a pale gum which upon trituration with pet. ether (60/80)/diethyl ether afforded a 2:1 isomeric mixture of 3,3-dianisyl-3H-[chromeno[6,5-b]benzofuran of formula (1a) and 3,3-dianisyl-3H-[chromeno[6,7-b]benzofuran of formula (1b) as a white solid (1.25g; 22%; m.pt. 120-49°C). Fractional recrystallisation of the mixture with pet. ether (60-80)/ethyl acetate afforded pure 3,3-dianisyl-3H-[chromeno[6,5-b]benzofuran] (1a) as a white solid (0.65g; m.pt. 159-60°C).





- 11 -

Example 2

3-Anisyl-3-(2,4-dimethoxyphenyl)-3H-[chromeno[6,5-b]benzofuran] (2a) and 3-anisyl-3-(2,4-dimethoxyphenyl)-3H-[chromeno[6,7-b]benzofuran] (2b)

A mixture of 2-hydroxydibenzofuran (0.62g; 0.0036mol), 1-anisyl-1-(2,4-dimethoxyphenyl)prop-2-yn-1-ol (1.0g; 0.0036mol) and acidic Alumina Brockmann I (5.0g) in benzene (40ml) was heated under reflux for 1.5h. The resulting dark mixture was filtered to remove the alumina which was washed with benzene, the combined filtrate and washings were evaporated and the residue flash chromatographed over silica (eluent: 20% ethyl acetate in hexane) to give a 2:1 isomeric mixture of 3-anisyl-3-(2,4-dimethoxyphenyl)-3H-[chromeno[6,5-b]benzofuran] of formula (2a) and 3-anisyl-3-(2,4-dimethoxyphenyl)-3H-[chromeno[6,7-b]benzofuran] of formula (2b) as a pale yellow glass of m.pt. 78-83°C. The isomers could not be separated.






Examples 3 to 6

Using preparative procedures analogous to those used in Examples 1 and 2, the following benzopyrans in accordance with the invention were also prepared:-

Example 3



3,3-Bis(4-dimethylaminophenyl)-3H-[chromeno[6,5-b]benzofuran] (3).




The structure of this compound was elucidated using spectroscopic methods (n.m.r). Its melting point was 195-197°C.

Example 4


3,3-Dianisyl-6-methyl-3H-[pyrano[2,3-b]-9H-5,6,7,8-tetrahydrocarbazole] (4a) and 3,3-dianisyl-10-methyl-3H-[pyrano[3,2-b]-9H-5,6,7,8-tetrahydrocarbazole] (4b)



The structures of these compounds were elucidated using n.m.r. spectra. The melting point of compound (4a) was determined as 147-155°C and that of compound (4b) was 205-207°C.

Example 53,3-Dianisyl-7H-[pyrrolo[2,3-f]chromene] (5)

The structure of this compound was determined from its n.m.r. spectrum. It exhibited a melting point of 145-152°C (decomp).


Example 6Spiro[dibenzo[a,d]cycloheptane-5,3'-3'H-chromeno[6,5-b]benzofuran] (6).

The structure of this compound was determined from its n.m.r. spectrum. It exhibited a melting point of 205°C (decomp).

- 15 -

Example 73-Anisyl-3-(2,4-dimethoxyphenyl)-6-methyl 3H-[chromeno[6,7-b]benzofuran] (7)

A solution of 2-hydroxydibenzofuran (18.42g;0.10mol) and 25-30% aqueous dimethylamine (22.0ml;0.122mol) in ethanol (100ml) was treated dropwise over 1h with 37% aqueous formaldehyde (9.0ml;0.1mol). The mixture was then heated at 100°C for 1h. The mixture was cooled to room temperature to precipitate 1-dimethylaminomethyl-2-hydroxydibenzofuran (7a). The product was washed firstly with 50% aqueous ethanol and then with ice-cold ethanol to give the product as tan coloured crystals (18.6g;77%), m.pt 113-5°C.




(7a)

A suspension of 1-dimethylaminomethyl-2-hydroxydibenzofuran (7a) (5.0g;0.021mol) in 10% aqueous potassium hydroxide (50ml) at 60°C (bath temp 100°C) was treated with portions of Nickel-Aluminium alloy (50:50) powder over 0.5h at such a rate as to maintain boiling. The mixture was heated at 100°C for a further 1h, then cooled to room temperature and filtered through a pad of Celite and the filter cake washed with water. Acidification of the filtrate with conc. HCl gave a precipitate. The aqueous suspension was extracted with ethyl acetate, the extracts were combined, dried and evaporated to afford the crude product (3.2g).


- 16 -

Purification using flash-chromatography over silica (eluent: 10% ethyl acetate in petroleum ether 60/80) gave 1-methyl-2-hydroxydibenzofuran (7b) (TLC; on silica; eluent 10% ethyl acetate in petroleum ether 60/80; $R_f = 0.2$) as an off-white solid, m.pt. $135.5-6.7^{\circ}\text{C}$.



A mixture of 1-methyl-2-hydroxydibenzofuran (7b) (0.60g; 0.0030mol), 1-anisyl-1-(2,4-dimethoxyphenyl)prop-2-yn-1-ol (0.90; 0.0030mol) and acidic Alumina Brockmann I (3.3g) in benzene (40ml) was heated under reflux for 15min. The resulting dark mixture was filtered to remove the alumina which was washed with benzene, the combined filtrate and washings were evaporated and the residue flash chromatographed over silica (eluent: 20% ethyl acetate in hexane) to give a pale gum which upon trituration with hexane gave 3-anisyl-3-(2,4-dimethoxyphenyl)-6-methyl 3H-[chromeno [6,7-b]benzofuran] (7) as a crude product (0.42g; 29%; m.pt. $158-65^{\circ}\text{C}$). Further purification by recrystallisation (hexane/ethyl acetate) gave the product as colourless microcrystals, m.pt. $173-4.7^{\circ}\text{C}$.


- 17 -

Example 8


3-Anisyl-3-(2,4-dimethoxyphenyl)-8,9-dimethyl-3H-[pyrano[3,2-e]benzothiophene] (8)

A solution of 5-bromo -2,3-dimethylbenzo[b]thiophene (3.61g; 0.015mol) in diethyl ether (40ml) under nitrogen was cooled to 0°C and treated dropwise over 5 min. with 2.5M n-butyl lithium (6.1ml; 0.0153mol). The resulting mixture was stirred for a further 20 min. then treated over 10 min. with a diethyl ether solution of tributyl borate (3.45g; 4.1ml; 0.0153mol) and allowed to warm to room temperature and stirred for 110min. The mixture was cooled to 10°C and treated with acetic acid (1.3ml; 0.0225mol) in one portion. After further cooling to 0°C, the mixture was treated dropwise with a solution of 30% hydrogen peroxide (1.7ml, 0.0165mol) in water (10ml) which resulted in an exotherm (T=15°C). The mixture was allowed to warm to room temperature and stirred for 2 hours. The mixture was poured into a saturated aqueous solution of ammonium sulphate containing ferrous ammonium sulphate and the organic phase washed until no colour was present. The organic phase was dried and evaporated to leave a tacky solid (contaminated with n-butanol) which upon trituration with petroleum ether (30/40) gave 5-hydroxy -2,3-dimethylbenzo[b]thiophene (8a). [TLC 20% ethyl acetate in hexane over silica; R_f 0.22] as a white solid (1.42g; 53%).

- 18 -



A mixture of 5-hydroxybenzothiophene (8a) (0.40g; 0.00224mol), 1-anisyl-1-(2,4-dimethoxyphenyl)prop-2-yn-1-ol (0.66g; 0.00224mol) and acidic Alumina Brockmann I (3.50g) in toluene (40ml) was heated under reflux for 1h. The resulting dark mixture was filtered to remove the alumina which was washed with toluene, the combined filtrate and washings were evaporated and the residue flash chromatographed over silica (eluent: 20% ethyl acetate in hexane) to give a yellow oil which crystallised upon trituration with hexane to afford 3-anisyl-3-(2,4-dimethoxyphenyl)-8,9-dimethyl-3H-[pyrano[3,2-e]benzothiophene] (8) as a white solid (0.32g; 31%) m.pt. 135-37°C.



- 19 -

The photochromic properties of the heterobenzopyran compounds of the present invention were tested by preparing, in conventional manner, by a direct casting process, 1.0 mm plates of a polyurethane host material of the type described in EP 0294056, incorporating the photochromic heterobenzopyran in a concentration of 0.3% w/w.

The resultant plates were illuminated under standard solar simulation conditions at Air Mass 2 at 21°C (see Parry Moon, J. Franklin Inst. 230, (1940), p 583-617). The measurements which were made on the samples in the darkened condition were taken when the samples had reached a steady state; this steady state was deemed to have been reached after 10 minutes in the darkened condition.

The results obtained are shown in Table 1.

Table 1 shows the difference between the unactivated and the activated photochromic article.

The first data column shows the induced optical density (IOD), measured at the integrated visible transmission (IVT), which is the log difference between the bleached transmission (BT) and the darkened transmission (DT).

$$\text{IOD (IVT)} = \log \text{BT (\%)} / \text{DT (\%)}$$

The two columns to the right of the table give both a subjective description of the bleached and darkened states and an objective description of colour using the universal Lab system (see reference at foot of Table 1). The Lab system is a method for representing colours mathematically and therefore numerically.

As will be seen from the results given in Table 1, the colouration of the samples in the darkened condition is a brown, yellow-brown, orange-brown or olive-green colouration.

Table 1
0.3 % w/w of photochromic in polyurethane plate (1mm)

Example	Induced Optical Density ¹ (Bleached Transmission/ Darkened transmission) (IVT)	Bleached colour ²		Darkened colour ²	
		a*	b*	a*	b*
2	0.730 (89.5/16.7)	colourless -0.87	0.70	brown 16.81	18.33
4b	0.286 (88.9/46.0)	colourless -0.99	2.59	yellow brown 15.43	60.42
5	0.650 (75.5/16.9)	pale brown -1.31	12.46	warm brown 26.24	49.14
6	0.642 (88.6/20.2)	colourless -1.10	1.55	orange/red brown 39.73	44.37
7	0.718 (91.1/17.4)	colourless -1.09	0.91	olive green -7.10	32.62
8	0.346 (89.5/40.4)	colourless -0.83	0.92	yellow brown 21.21	51.42


¹ 10 minutes darkening under Xenon arc filtered to Air-Mass 2 at 21°C.

² L*a*b* system (DIN 6174, Commission Internationale de L'Eclairage 1976) developed by Judd and Hunter (ref. G.J. Chamberlin and D.G. Chamberlin, Colour: Its Measurement, Computation and Application, ed. L.C. Thomas, Heyden 1980, ch. 4.

- 21 -

CLAIMS:

1. A heterobenzopyran compound of general formula (I)



wherein R_1 represents a five-membered heterocyclic group containing one or more hetero atoms and fused either to the f-face or the g-face of the benzo moiety of the benzopyran skeleton, the said heterocyclic group being fused in such a manner that the hetero atom in the heterocyclic group is linked directly to a carbon atom on the said benzo moiety, and, optionally, the said heterocyclic group has fused thereto a further carbocyclic or heterocyclic group or is substituted with a group of formula R_4 as defined below;

each of R_2 and R_3 , which may be the same or different, independently represents a carbocyclic or heterocyclic group, or R_2 and R_3 taken together with the carbon atom to which they are attached form a carbocyclic or heterocyclic ring system; and

R_4 represents a hydrogen atom or a substituent selected from alkyl, alkoxy, aryl, aryloxy, heteroaryl, halogen, substituted or unsubstituted amino, azo, imino, amide, ester, cyano, trifluoromethyl or nitro.

- 22 -

2. A heterobenzopyran compound according to claim 1, wherein the five membered heterocyclic ring in the group R_1 is a furan ring, a pyrrole ring or a thiophene ring, preferably with the hetero-atom attached to the 7-position of the benzopyran skeleton.

3. A heterobenzopyran compound according to claim 1 or 2, wherein the heterocyclic ring in the group R_1 has a benzene ring fused thereto, or a cyclohexane ring fused thereto, or carries one or more alkyl substituents.

4. A heterobenzopyran compound according to claim 2 or 3, wherein the ring nitrogen atom of the pyrrole ring is substituted with an alkyl group, preferably a methyl group.

5. A heterobenzopyran compound according to any one of the preceding claims, wherein each of the R_2 and R_3 substituents is chosen from a phenyl group, a 4-trifluoromethyl-phenyl group, a 4-alkoxyphenyl group, preferably 4-methoxyphenyl, a 2,4-di(alkoxy)phenyl group, preferably 2,4-dimethoxyphenyl or a 4-dialkylamino-phenyl group, preferably 4-dimethylamino-phenyl.

6. A heterobenzopyran compound according to any one of claims 1 to 4, wherein the R_2 and R_3 substituents together with the carbon atom to which they are attached form a spiro-dibenzocycloheptenyl substituent, or a spiro-adamantyl substituent or a spiro-norbornyl substituent.

7. A heterobenzopyran compound according to any one of the preceding claims, wherein R_4 is a hydrogen atom or a methyl group.


8. 3,3-Dianisyl-3H-[chromeno[6,5-b]benzofuran].

9. 3,3-Dianisyl-3H-[chromeno[6,7-b]benzofuran].

10. 3-Anisyl-3-(2,4-dimethoxyphenyl)-3H-[chromeno[6,5-b]benzofuran].

- 23 -


11. 3-Anisyl-3-(2,4-dimethoxyphenyl)-3H-[chromeno[6,7-b]benzofuran].
12. 3,3-Bis(4-dimethylaminophenyl)-3H-[chromeno[6,5-b]benzofuran].
13. 3,3-Dianisyl-6-methyl-3H-[pyrano[2,3-b]-9H-5,6,7,8-tetrahydrocarbazole].
14. 3,3-Dianisyl-10-methyl-3H-[pyrano[3,2-b]-9H-5,6,7,8-tetrahydrocarbazole].
15. 3,3-Dianisyl-7H-[pyrrolo[2,3-f]chromene].
16. Spiro[dibenzo[a,d]cycloheptane-5,3'-3'H-chromeno[6,5-b]benzofuran].
17. 3-Anisyl-3-(2,4-dimethoxyphenyl)-6-methyl 3H-[chromeno[6,7-b]benzofuran].
18. 3-Anisyl-3-(2,4-dimethoxyphenyl)-8,9-dimethyl-3H-[pyrano[3,2-e]benzothiophene].
19. A process for preparing a heterobenzopyran compound of formula (I) as defined in claim 1, which process comprises condensing a hydroxy compound of general formula (III)



(III)

- 24 -

wherein R_1 and R_4 are as defined in claim 1, with the hetero atom in the heterocyclic ring of the group R_1 being located in the para- or meta- position relative to the hydroxy group on the benzene ring, with a propargyl alcohol of general formula (IV)



wherein R_2 and R_3 are as defined in claim 1, in the presence of acidic alumina; trifluoroacetic acid or another like acidic catalyst.

20. A photochromic article comprising a polymeric host material having a heteropyran compound as defined in any one of claims 1 to 18 incorporated therein or applied thereto.

21. A photochromic article according to claim 20, wherein the polymeric host material is selected from polymers of polyol (allyl carbonate) monomers, polyacrylates, poly(alkylacrylates), cellulose acetate, cellulose triacetate, cellulose acetate propionate, cellulose acetate butyrate,

- 25 -

poly(vinyl acetate), poly(vinyl alcohol), polyurethanes, polycarbonates, polyethylene terephthalate, polystyrene, styrene/methylmethacrylate copolymers, styrene/acrylonitrile copolymers, and polyvinylbutyral.

22. A photochromic article according to claim 21, wherein the polymeric host material is a polyurethane or a polymer of diethyleneglycol bis (allyl carbonate).

23. A photochromic article according to claim 20, 21 or 22, wherein the amount of heterobenzopyran compound is from 0.01 to 0.5% by weight, based on the weight of the polymeric host material.

24. A photochromic article according to any one of claims 20 to 23, comprising a further photochromic compound selected from spiro(indoline)naphthoxazines, spiro(indolino)pyrido benzoxazines, spiro(indolino)benzoxazines, and naphthopyrans.

25. A photochromic article according to claim 24, wherein the further photochromic compound is present in an amount of from 0.001 to 0.5% by weight, based on the weight of the polymeric host material.

26. A photochromic article according to any one of claims 20 to 25, which is in the form of a lens.

27. A photochromic article according to claim 26, wherein the lens is an ophthalmic lens.

INTERNATIONAL SEARCH REPORT

 International Application No
 PCT/GB 94/01758

A. CLASSIFICATION OF SUBJECT MATTER

 IPC 6 C07D491/04 C07D493/04 C07D495/04 G03C1/72 /
 /(C07D491/04,311:00,209:00),(C07D493/04,311:00,307:00),
 (C07D495/04,311:00,333:00)

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C07D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P,X	EP,A,0 562 915 (ESSILOR INTERNATIONAL, CIE) 29 September 1993 see claims 1-16; examples 1-8 ---	1-7, 19-27
Y	EP,A,0 401 958 (TOKUYAMA SODA K.K.) 12 December 1990 see claims 1-14; table 8 ---	1-27
Y	WO,A,93 10112 (PPG INDUSTRIES, INC.) 27 May 1993 cited in the application see page 6, line 23 - page 6, line 31; claims 1-19 --- -/--	1-27

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

21 October 1994

Date of mailing of the international search report

-9. 11. 94

Name and mailing address of the ISA

 European Patent Office, P.B. 5818 Patentlaan 2
 NL - 2280 HV Rijswijk
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
 Fax (+31-70) 340-3016

Authorized officer

Herz, C

INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 94/01758

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	J. PHOTOCHEM. PHOTOBIOLOG. A vol. 49, no. 1-2, 1989 pages 75 - 78 YA. N. MALKIN ET AL. 'Quantitative Study of the Photostability of Spiropyrans' * page 78, formula 6 and 9 * ---	1-3,7
X	IZV. AKAD. NAUK SSSR, SER. KHIM. (TRANSL.) vol. 39, no. 2, 1990 pages 236 - 242 YA. N. MALKIN ET AL. 'Quantitative Study of the Photostability of Spiropyrans' * page 240, formula 6 and 9 * ---	1-3,7
X	IZV. AKAD. NAUK SSR, SER. KHIM. (TRANSL.) vol. 38, no. 11, 1989 pages 2297 - 2302 T.B. KRASIEVA ET AL. 'Photochemistry of Spiropyrans of the Dithiolane Series with polycondensed Chromene Fragments' * page 2298, formula VI and X * ---	1-3,7
X	IZV. AKAD. NAUK SSSR, SER. KHIM. (TRANSL.) vol. 37, no. 7, 1988 pages 1385 - 1387 S.M. ALDOSHIN ET AL. 'Effect of the Nature of the Heteroatoms in the Spiro Group on the Structure of Spiropyrans and an X-Ray Study of Spiropyran of the Dithiolane Series C ₁₇ H ₁₆ O ₂ S ₂ ' * compound of formula (I) * -----	1-3,7

INTERNATIONAL SEARCH REPORT
(information on patent family members)

International Application No
PCT/GB 94/01758

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-0562915	29-09-93	FR-A- 2688782	24-09-93
		AU-B- 3537093	23-09-93
		JP-A- 6135967	17-05-94

EP-A-0401958	12-12-90	JP-A- 3011075	18-01-91
		JP-A- 3011074	18-01-91
		US-A- 5106998	21-04-92
		US-A- 5349065	20-09-94

WO-A-9310112	27-05-93	US-A- 5066818	19-11-91
